



# RUSTICUS

**description** Uncoated papers and boards made with E.C.F. pulp. Felt marked on both sides. Available in five shades.

**range**

size	grain	substance
72x101	LG	95 140 200 240 280

**technical features**  
ref. standard/instrument  
unit of measure

substance	VSA	opacità	Wax pick test	Taber stiffness 15°	
ISO 536	ISO 534	ISO 2471	UNI 9073	ISO 2493	
g/m <sup>2</sup>	cm <sup>3</sup> /g	%	n° (Dennison)	mN	
				long±10%	trasv±10%
95 ± 3%	1,5	91 ± 2	≥ 14	8	4
140 ± 3%	1,5	94 ± 2	≥ 14	14	8
200 ± 4%	1,5	–	≥ 14	100	50
240 ± 5%	1,5	–	≥ 14	190	80
280 ± 5%	1,5	–	≥ 14	270	110

Brightness (col. Neve) ISO 2470 (R457) - 92% ± 2  
Relative Humidity 50% ± 5 ref. TAPPI 502-98

**ecological features**



ELEMENTAL  
CHLORINE  
FREE  
GUARANTEED



ACID FREE



ISO 9706



CE 94 / 62



**notes** The products could show light differences in papershade and look due to natural raw materials used. The product is completely biodegradable and recyclable. Special runs available upon request.

Fabriano is a trademark of Fedrigoni SpA  
The Company reserves the right to modify the technological features of the product in relation to market requirements.

Rusticus papers and boards are ideal for any kind of publishing, packaging and commercial printing. They are held in high regard for packaging, special publications, brochures, booklets and coordinated graphic materials.

applications

Can be used without problems with the main printing systems: letterpress, offset, blind embossing, hot foil stamping, thermography and screen printing. The macro-porous surface suggests the use of oxidative drying inks. The characteristic felt marking requires specific printing pressure settings.

printing  
suggestions

Varnishing and plastic laminating must be assessed in advance. The varnishing coated with an offset machine is almost fully absorbed and therefore does not improve gloss or protection. Screen-printing varnishing achieves better results, although it is often necessary to perform two shots to achieve a distinctly evident result. The surface roughness typical of felt marked papers may give rise to micro defects with plastic laminating caused by incomplete adhesion of the film to the substrate. Good results with major processing operations such as: cutting, die-cutting, scoring, folding and glueing.

converting  
suggestions